# WEICONLOCK® AN 302-80 Pipe and Thread Sealing



### higher viscosity high strength hard to disassemble

Pipe and Thread Sealing for passive materials



## **Technical Data**

Colour	green
For threaded joints up to	M36
Max. gap bridging	0,2 mm
Breakaway strength (Thread)	15 - 20 Nm
Prevailing stregth	25 - 30 Nm
Shear strength Nmm <sup>2</sup> (DIN 54452)	20 - 30 N/mm <sup>2</sup>
Handling strength at room temperature	5 - 10 min.
Final strength (100%) after	6 - 12 h
Temperature resistance	-60 to +200 °C

\*Strength values determined with stainless steel screws M 10, thickness of nut: 0,8 • d

### Surface pre-treatment

In general, WEICONLOCK does not require special pre-treatment as slightly oily surfaces (e.g. on as received parts) will be tolerated. However, best results will be achieved on cleaned, degreased parts (use WEICON Surface Cleaner). If required, the parts should be slightly roughened.

#### Processing

WEICONLOCK is ready for use and should be applied evenly direct from the bottle/tube with the dispensing tip (avoid direct contact of dispensing tip with metal). Apply WEICONLOCK in circular motions on the thread. Screw pipe threads together and tighten until desired

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG WEICON Middle East L.L.C. (Headquarters) United Arab Emirates phone +971 4 880 25 05

Germany phone +49 (0) 251 9322 0 info@weicon.de WEICON SA (Pty) Ltd

South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

info@weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 nfo@weicon.c www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weiconcz.cz

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

30280020	WEICONLOCK® AN 302-80 Pipe and Thread
	Sealing 20 ml
30280150	WEICONLOCK® AN 302-80 Pipe and Thread
	Sealing 50 ml
30280200	WEICONLOCK® AN 302-80 Pipe and Thread
	Sealing 200 ml

orientation. When using as flange sealing apply a continuous bead on one side. Join and tighten parts quickly. Do not pour back into the bottle any WEICONLOCK fluid which had contact with metal; even smallest metal particles will cause the content of the bottle to cure. In series construction, the use of manual or automatic

WEICONLOCK can be stored in the unopened original container for at least 24 months at room temperature. Keep away from heat sources and direct sunlight. The air in the bottle/tube keeps

When using WEICON products, the physical, safety technical,

# Accessories:

Available sizes:

applicators is recommended.

WEICONLOCK liquid. Safety and health

Storage

30955172 30955179

Dosing Tips, Size 1 Dosing Tips, extra thin

> WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weig